

# GFZ2

## Isostatic Powder Press for Tableware



### Advantages

---

- Precision and durability
- Energy efficiency
- Productivity
- Tailored to our DORST tool systems
- Flexibility

## Technical information

---

- Closing force: 7000 kN
- Isostatic pressure: 300 bar

### Pressing heads

- Number: 1

### Pressing tools

- Number: 2

### Maximum size of article (pressed, green)

- Circular articles (diameter): max. 480 mm
- Square articles (side length): max. 410 x 410 mm
- Oval articles (length x width): max. 550 x 410 mm
- Rectangular articles (length x width): max. 505 x 355 mm
- Article height: max. 275 mm

### Output

- Circular articles (depending on granular material and article shape): approx. 150 - 200 pcs/h
- Non-circular articles (depending on granular material and article shape): approx. 100 - 150 pcs/h

### Fettling machines

- can be combined with robot fettling systems RUP2 for circular and non-circular articles

## Keyfacts

---

- Strong closing cylinder with centered clamping platens and tool locating blocks for permanent precision
- Powerful vacuum and compressed air filling system (optional) for quick and safe filling of all kinds of article geometries
- Closed-loop controlled pressure intensifier for the isostatic pressure (optional) including filling monitoring of the pressing tool (empty pressing/double pressing)
- Field-tested usability

### DORST tool system

- Static pre-compaction of the granules.
- Optimum use of the membrane space (energy efficiency)
- Adjustment of the thickness of the article layer during operation
- Long service life of the membranes
- Quick and easy tool change due to centered tool halves

## Characteristics

---

- Sound insulation (optional) for improved occupational health and safety
- Dust extraction (optional) for improved occupational health and safety
- Service router (optional) for quick remote support provided by our DORST Customer Service Office

## Technologies

---

- Isostatic pressing of ceramic granules
- Vacuum filling and filling of the pressing tools under compressed air
- Static pre-compaction of the pressing granules